

HumiSeal[®] Standard Solvent Based Thinners Technical Data Sheet

When necessary, the viscosity of HumiSeal[®] coatings may be adjusted for application purposes, using a compatible thinner from the table below. HumiSeal[®] Thinners are blends of solvents, formulated to maintain the original system balance when added to the correct coating type. These HumiSeal[®] Thinners are in full compliance with the RoHS Directive 2002/95/EC.

Typical Physical Properties of HumiSeal[®] Thinners

Thinner	64	73	503	505	521	535
Compatible HumiSeal [®] Coatings	2A64	1B73	1B12, 1B31, 1B66, 1B73	1R32, 1R32A-2	1A20, 1A27, 1A33, 1B31, 1B66, 1B73, 1R32	2A53
Relative Evaporating Rate (BuAc=1)	0.89	1.0	3.77	1.65	0.60	1.50
Specific Gravity	0.95 ± 0.01	0.88 ± 0.01	0.85 ± 0.01	0.83 ± 0.01	0.87 ± 0.01	0.87 ± 0.01
Boiling Point (°C)	110	127	82	117	137	110
Vapour Pressure (mmHg)	9.1	8.0	45.4	15	19.4	45.4
Vapour Density (Air=1)	3.4	4.0	4.0	3.5	3.6	4.0
Flash Point (°C) TCC	5	27	-1	14	27	5
VOC (grams/litre)	950	882	850	830	868	868
Shelf Life, DOM	24 months					
Colour	Clear					

Directions for Use

Add HumiSeal[®] Thinner to a compatible coating until the desired viscosity is obtained.

Handling Precautions

HumiSeal[®] Thinners are flammable and the following standard safety precautions should be observed:

- Use only in well ventilated areas.
- Protective gloves and goggles should be worn.
- In case of prolonged skin contact, wash with water.
- In case of eye contact, flush with water and contact physician.
- Avoid prolonged breathing of vapours.
- Unused portions of HumiSeal[®] products must be disposed of in strict compliance with Local, State, and Federal laws governing such matters.
- Consult the Material Safety Data Sheet (MSDS/SDS) for more specific product information.

Contact HumiSeal®

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.